



# MAXEPOX<sup>®</sup>

## MORTER -V

### WATER-BASED EPOXY COATING FOR VERTICAL SURFACES

#### DESCRIPTION

**MAXEPOX<sup>®</sup> MORTER -V** is a coloured and two-component water-based epoxy coating suitable for protective and decorative coating of floors, ceilings, and both horizontal and vertical surfaces in general. It is available in two different versions:

- **MAXEPOX<sup>®</sup> MORTER -V MATT** for an eggshell, matt finish.
- **MAXEPOX<sup>®</sup> MORTER -V GLOSS** for a smooth glossy finish.

#### APPLICATION FIELDS

- Protective and decorative coatings for vertical concrete surfaces, cement mortars or gypsum plasters walls or other surfaces in hospitals, garages, dairies, butcheries, kitchens, power plants, chemical industrial facilities, warehouses, etc.
- Protective coating of metal surfaces, steel and other polished surfaces.
- Priming for solvent-free epoxy-based systems.
- Anti-dust protective coating for warehouses, car parking areas, and industrial factories.
- Sealing of porous surfaces or with residual humidity before applying solvent-based polyurethane liquid waterproofing membranes.

#### ADVANTAGES

- Excellent adhesion to concrete and steel.
- Elastic modulus compatible with the thermal movements of the substrate.
- High mechanical strengths, providing a coating with an excellent abrasion resistance.
- Suitable for substrates with low level of humidity.
- Easy to clean.
- Environmentally friendly: non-toxic, epoxy-based, non-flammable and solvent-free product. Suitable for poor ventilated areas.

#### APPLICATION INSTRUCTIONS

Surface to be coated must be structurally sound, firm, without cement laitance and as uniform as

possible, and preferably with a slight roughness, i.e. open textured surface. It must be dry, clean and free of paints, coatings, efflorescence, loose particles, grease, oils, curing agents, form release agents, dust, gypsum plasters, organic growth or any other contaminants that may affect to adhesion of the product.

Avoid application on substrates subject to rising damp. Substrate could contain a certain amount of humidity but it cannot be applied on wet surfaces or with flowing water.

Consult our technical note "*Preparation of concrete surfaces for application of epoxy-based coatings*" for further information.

For cleaning and preparing the substrate, preferably in case of the smooth and/or poorly absorbent concrete and cement mortars, provide a mechanical texturing by abrasive disc, dry sand-blasting, scarification or other abrasive method to achieve at least a slightly textured surface, not being desirable aggressive mechanical or chemicals means. Finally, vacuum the dust and loose particles.

Before coating application, all small voids, holes, honeycombs, cavities, once opened must be patched with the **MAXEPOX<sup>®</sup> CEM** epoxy-cement mortar (Technical Bulletin No. 197) or with the **MAXEPOX<sup>®</sup> JOINT** epoxy-based mortar (Technical Bulletin No. 237). Cold joints, tie holes, and static cracks without movement, once opened and routed to a minimum depth of 2 cm, must be repaired with the **MAXREST<sup>®</sup>** (Technical Bulletin No. 2) structural repair mortar to provide an even surface.

Rebars and other metal elements exposed during the substrate preparation should be cleaned and passivated with **MAXREST<sup>®</sup> PASSIVE** (Technical Bulletin No. 12), while non-structural and surface iron elements must be cut to a depth of at least 2 cm and then covered with a suitable repair mortar.

Expansion joints and fissures/cracks subject to movements, once opened must be sealed with any suitable sealant of **MAXFLEX<sup>®</sup>** range.

### Concrete and cement mortar:

For cleaning and preparing the substrate, preferably in case of the smooth and/or poorly absorbent concrete and cement mortars, provide a mechanical texturing by abrasive disc, dry sand-blasting, scarification or other abrasive method to achieve at least a slightly textured surface, not being desirable aggressive mechanical or chemicals means. Finally, vacuum the dust and loose particles.

### Steel and other non-porous surfaces:

Metal surfaces should be cleaned to remove all traces of corrosion, and must be degreased, dry and free of dust. Use sand or shot blasting to Sa 2½ grade (near to white metal) according to Swedish Standards or equivalent. On metal surfaces pay attention to drying conditions, because oxidation could arise when drying process is not very fast.

### Mixing

**MAXEPOX® MORTER -V** is supplied as a pre-weighed two-component set.

Premix the components separately, and then the hardener, component B, is poured into the resin, component A. In order to ensure the proper reaction of the two components make sure all of component B is added.

Mixing manually or preferably using a low speed drill (300-400 rpm. maximum), fitted with a mixer suitable for liquids for about 2-3 minutes until achieving a homogeneous product in colour and appearance. Do not mix for prolonged period nor use high-speed mixer, which may heat the mixture or introduce air bubbles.

Check Technical Data Table for product pot life (2 hours at 20° C). This value increases with lower temperatures or small quantities of mixture, and reduces with higher temperatures.

### Application

Work **MAXEPOX® MORTER-V** into the prepared substrate to fill and cover all micropores and other small voids, using preferably a solvent-resisting brush or roller. When using an air-less spray equipment dilute with a sufficient amount (up to 5%, by volume) of water to allow the easy application of the product.

### Standard priming:

In order to improve the penetration of the product into substrate and provide a better adhesion on porous substrates such as standard concrete, apply a first coat of **MAXEPOX® MORTER -V** diluted with 5% of water with a consumption of about 0,20-0,30 kg/m<sup>2</sup>, depending on porosity of substrate.

### Coating (smooth surface finish):

Apply a first coat of **MAXEPOX® MORTER -V** with a consumption from 0,20 to 0,30 kg/m<sup>2</sup>, depending on the porosity of the substrate. Once dried, i.e. from 6 to 12 hours, depending on ventilation and ambient conditions, apply a second layer with the same coverage. Do not leave more than 24 hours between coats. If this time does elapse before the following coat is applied or the surface has been in contact with water or other liquids, then lightly sand the surface before proceeding with coats.

### Priming for solvent-free epoxy coating and other systems:

**MAXEPOX® MORTER -V MATT** can be used as primer for solvent-free epoxy systems over concrete or cement mortars.

Avoid application on substrates subject to rising damp. Substrate could contain a certain amount of humidity but it cannot be applied on wet surfaces or with flowing water. Apply the priming coat of **MAXEPOX® MORTER -V MATT** with diluted with 5% of water with a consumption of about 0,20-0,25 kg/m<sup>2</sup>, depending on porosity of substrate. It is particularly recommended as a primer for **MAXEPOX® 800** coating (Technical Bulletin No. 35).

**MAXEPOX® MORTER -V MATT** can also be applied over other types of paints or coatings with or without solvents, once those have hardened, and thus, provide a good adhesion between the hardened coating and the new one. Performance over several cured substrates such as epoxy, polyester, polyurethane, bitumen, asphalt slurries, etc, is good, although a preliminary test on-site to check bonding is recommended.

Before applying the finish coating, it is required that the **MAXEPOX® MORTER -V MATT** coating applied as primer is dry, that is, the water has evaporated and the polymerising has at least started. For this reason, a good air renovation, low humidity and a temperature above 10°C are required.

### Application conditions

Do not apply in rain or when rain, contact with water, condensation, dampness and dew is expected within the first 24 h after the application. Optimum application temperature range is from 10 °C to 30 °C. Do not apply with substrate and/or ambient temperature is at or below 10 °C, or when are expected to fall below 10 °C within 24 h after application. Do not apply to frozen or frost-covered surfaces.

Ambient and surface temperature must be at least 3 °C higher than dew point. Do not apply with R.H.

higher than 80 %. Measure the relative humidity and dew point before applying the product. With low temperatures, high humidity levels or both, use dry and warm air in order to get the suitable conditions, such as with an electric powered air blower system.

Temperatures above 30 °C lead a quick-setting between components and heat production, so the pot life is greatly reduced.

## Curing

Allow **MAXEPOX<sup>®</sup> MORTER -V** to cure for at least 5 days at 20 °C and 50% R.H. before putting into service to heavy traffic. Applications at lower temperatures, high humidity and/or poor ventilation conditions require longer drying and curing times.

## Cleaning

All mixing and application tools, and equipment must be cleaned immediately with water after use. Once product cures, this can only be removed by mechanical means.

## CONSUMPTION

Estimated consumption for **MAXEPOX<sup>®</sup> MORTER -V** varies from 0,20 to 0,30 kg/m<sup>2</sup> per coat, i.e., a total consumption from 0,40 to 0,6 kg/m<sup>2</sup>, applied in two coats.

These figures are for guidance only and may vary depending on porosity, texture and conditions for substrate, and application method. Perform a preliminary test on-site to ascertain the total consumption exactly under jobsite conditions.

## IMPORTANT INDICATIONS

- For interior use only. Under sun light exposure, some colour variations or discolouration can take place.
- Do not apply on substrates subject to rising humidity or negative water pressure.
- Avoid contact with water, damp, dew, condensation, etc for at least 72 hours after application. Relative humidity must not exceed 80%. If so, an improper curing or loss of colour intensity may happen.
- Allow new concrete and mortar to cure a minimum of 28 days before applying **MAXEPOX<sup>®</sup> MORTER -V**
- Use the recommended A to B mixing ratio.

- Observe the recommended consumptions per coats.
- Do not add solvents, thinners, admixtures, or other compounds.
- For other uses not specified in this Technical Bulletin, further information or questions regarding the application of the product, consult the Technical Department.

## PACKAGING

**MAXEPOX<sup>®</sup> MORTER -V** is supplied in pre-weighed two-component sets of 10 kg and 20 kg. It is available in 5 different standard colours, and two versions (matt and gloss): green, red, grey, white and brown. Other colours are available upon special request.

## STORAGE

Six months in its unopened and undamaged original sealed packaging. Store in a cool, dry and covered place, protected from moisture, frost and away from direct exposure to sunlight, with temperatures between 5 °C and 30 °C.

Storage at temperatures below 5 °C may lead the crystallisation of product components. Should this happen, it must be heated slowly at moderate temperature while it is regularly stirred until achieving its homogeneous and original lump-free appearance.

## SAFETY AND HEALTH

**MAXEPOX<sup>®</sup> MORTER -V** is not a toxic product but direct contact with skin and eyes must be avoided. Use rubber gloves and safety goggles when handling, mixing and applying the product. In case of contact with skin, wash affected area with soap and water. In case of contact with eyes, rinse immediately thoroughly with clean water but do not rub. If the irritation persists, seek medical assistance. Do not inhale vapors from heating and combustions process. If ingested, seek immediate medical assistance. Do not induce vomiting.

Consult the Material Safety Data Sheet for **MAXEPOX<sup>®</sup> MORTER -V**.

Disposal of the product and its packaging should be carried out according to the current official regulations and it is the responsibility of the final user of the products.

## TECHNICAL DATA

Product characteristics	
General appearance and colour for component A	Coloured, homogeneous liquid
General appearance and colour for component B	Translucent-yellowish liquid
A:B mixing ratio for matt/ gloss version, (by weight)	4:1 / 5:1
Application and curing conditions	
Application conditions, T (°C) / R.H. (%)	> 10 / < 80
Pot life at 10 °C/ 20 °C/ 30 °C, (min)	180 / 120 / 60
Tack-free drying-time at 20 °C, (hours)	2 - 4
Waiting time between coats at 20 °C, (hours)	6-12 (max.) to 24 (min.)
Total curing time at 10 °C/ 20 °C/ 30 °C, (days)	8 / 5 / 3
Cured product characteristics	
Persoz Hardness 1 / 2 / 7 / 14 days at 20 °C (s)	60 / 90 / 220 / 255
Erichssen Extensibility 7 / 14 days, DIN 52156	7,0 / 5,5
Water resistance over aluminium at 20°C / 98 °C (months/hours)	6 / 6
Gardner Shine. Matt/Glossy version	22 / 65
Slip/skid resistance value, UNE-ENV 12633 (Rd)	Class 3
Flash point, (°C)	Non flammable
Consumption*	
Consumption per coat / total application, (kg/m <sup>2</sup> )	
- Priming for 100% solid, epoxy or polyurethane systems:	0,20-0,30
- Smooth finishing.	0,20-0,30 / 0,40-0,60

(\*) These figures are for guidance only and may vary depending on porosity, texture and conditions for substrate, and application method. Perform a preliminary test on-site to ascertain the total consumption exactly under jobsite conditions.

## GUARANTEE

The information contained in this leaflet is based on our experience and technical knowledge, obtained through laboratory testing and from bibliographic material. **DRIZORO®**, **S.A.U.** reserves the right to introduce changes without prior notice. Any use of this data beyond the purposes expressly specified in the leaflet will not be the Company's responsibility unless authorised by us. We shall not accept responsibility exceeding the value of the purchased product. The data shown on consumptions, measurement and yields are for guidance only and based on our experience. These data are subject to variation due to the specific atmospheric and jobsite conditions so reasonable variations from the data may be experienced. In order to know the real data, a test on the jobsite must be done, and it will be carried out under the client responsibility. We shall not accept responsibility exceeding the value of the purchased product. For any other doubt, consult our Technical Department. This version of bulletin replaces the previous one.



### DRIZORO, S.A.U.

C/ Primavera 50-52 Parque Industrial Las Monjas  
28850 TORREJON DE ARDOZ – MADRID (SPAIN)  
Tel. 91 676 66 76 - 91 677 61 75 Fax. 91 675 78 13  
e-mail: info@drizoro.com Web site: drizoro.com

ISO 9001  
ISO 14001

BUREAU VERITAS  
Certification



ES045396-1/ES045397-1